

CHI MEI CORPORATION

59-1 SAN CHIA, JEN TE, TAINAN 717 TW

PA-765A(+)**Acrylonitrile Butadiene Styrene (ABS), "Polylac", furnished as pellets**

Color	Min Thk (mm)	Flame Class	HWI		RTI	RTI	RTI
			HWI	HAI	Elec	Imp	Str
ALL	1.5	V-1	-	-	85	80	85
	2.1	V-0, 5VB	3	0	85	80	85
	2.5	V-0, 5VA	3	0	85	80	85
	3.0	V-0, 5VA	0	0	85	80	85

Comparative Tracking Index (CTI): **1**

Inclined Plane Tracking (IPT): -

Dielectric Strength (kV/mm): -

Volume Resistivity (10^x ohm-cm): -High-Voltage Arc Tracking Rate (HVTR): **2**High Volt, Low Current Arc Resis (D495): **7**

Dimensional Stability (%): -

(+) - Optional prefix or suffix; may be used to denote usage of 0-0.5 percent acid scavengers. For PC-110(+), Optional the suffix except L, N, U, V, T, and F. For Grade PB-1202(+), Maybe none or replace by one alphabet to indicate the color.

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents.
ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1983-06-23
Last Revised: 2011-07-12

© 2012 UL LLC



IEC and ISO Test Methods

Test Name	Test Method	Units	Thickness	
			Tested (mm)	Value
Flammability	IEC 60695-11-10, IEC 60695-11-20	Class (color)	1.5	V-1 (ALL)
			2.1	V-0, 5VB (ALL)
			2.5	V-0, 5VA (ALL)
			3.0	V-0, 5VA (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-2	kJ/m ²	-	-

© 2012 UL LLC