

LANXESS AG

CHEMPARK DORMAGEN, BU HPM, BUILDING F46, DORMAGEN 41538 DE

B30S+(f1)

Polyamide 6 (PA6), "DURETHAN", furnished as pellets

Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
NC	0.38	V-2	-	-	-	-	-
ALL	1.0	-	-	-	105	-	-
	1.5	V-2	4	0	105	65	75
	3.0	V-2	3	0	105	65	75
	6.0	V-2	2	0	105	65	75

Comparative Tracking Index (CTI): **0**

Inclined Plane Tracking (IPT): -

Dielectric Strength (kV/mm): **27**Volume Resistivity (10^x ohm-cm) : **14**High-Voltage Arc Tracking Rate (HVTR): **0**

High Volt, Low Current Arc Resis (D495): -

Dimensional Stability (%): 0.3

(f1) - Suitable for outdoor use with respect to exposure to Ultraviolet Light, Water Exposure and Immersion in accordance with UL 746C.**+ - Material designations may be followed by suffix numbers and/or letter(s) denoting color.**

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents.
ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1969-11-12
Last Revised: 2005-04-15

© 2012 UL LLC



IEC and ISO Test Methods

Test Name	Test Method	Units	Thickness	
			Tested (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	0.38	V-2 (NC)
			1.5	V-2 (ALL)
			3.0	V-2 (ALL)
			6.0	V-2 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-2	kJ/m ²	-	-

© 2012 UL LLC